

# PATENT SPECIFICATION

(11) 1 532 641

1 532 641

- (21) Application No. 17622/75 (22) Filed 28 April 1975  
 (23) Complete Specification filed 27 April 1976  
 (44) Complete Specification published 15 Nov. 1978  
 (51) INT CL<sup>2</sup> C22C 38/18  
 (52) Index at acceptance



C7A 71X 741 748 770 77X 780 78Y A249 A25Y A272 A27X  
 A28X A28Y A30Y A313 A316 A319 A320 A323 A329  
 A339 A349 A35Y A364 A366 A369 A389 A409 A439  
 A459 A509 A529 A533 A535 A537 A539 A53Y A541  
 A543 A545 A547 A549 A54X A55Y A565 A568 A571  
 A574 A577 A579 A57Y A58Y A595 A599 A609 A61Y  
 A627 A629 A671 A673 A675 A677 A679 A67X A681  
 A683 A685 A687 A689 A68X A693 A694 A695 A696  
 A697 A698 A699 A69X A70X

(72) Inventor R. T. CUNDILL

## (54) ALLOY STEEL POWDERS

(71) We, BRITISH STEEL CORPORATION, a Corporation incorporated and existing under the Iron and Steel Act 1967 whose principal office is at 33 Grosvenor Place, London, S.W.1 do hereby declare the invention for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—

This invention relates to hardenable chromium alloy steel powders and to the production of densified heat treated components from such powders. Examples of typical components are automotive products such as gears, shafts and bearings.

It is known to produce metal powder by causing jets of water to strike a freely falling stream of molten metal to atomise the same. Normally, the metal powder produced is subjected to an annealing treatment to improve compressibility; compacts produced from the powder are then sintered and, for higher duty applications, the sintered compacts may be densified by hot or cold working.

Typical heat treatable steels include elements such as silicon, manganese, chromium. If a melt of such a steel is water atomised, oxides are formed which are not reduced during subsequent sintering and which result in reduced ductility, impact strength and fatigue strength of components produced from the powder.

According to the present invention in one aspect, a finely divided annealed steel powder consists by weight of up to 1.5% carbon, 1.0 to 2.0% chromium, less than 0.05% silicon, less than 0.1% manganese and either one or a combination of two or more of the following elements: 0.2 to 1.0% molybdenum, 0.2 to 1.0% nickel, up to 0.3% phosphorus and up to 1.0% copper, the balance, apart from impurities, being iron.

A preferred powder consists by weight of 0.9 to 1.1% carbon, 1.4 to 1.6% chromium, less than 0.02% silicon, less than 0.05% manganese, and either one or a combination of two or more of the following elements: 0.5 to 0.6% molybdenum, 0.5 to 0.6% nickel, up to 0.2% phosphorus and 0.5 to 0.6% copper, the balance, apart from impurities, being iron.

A method of producing a hardenable chromium alloy steel powder having an oxygen content of less than 250 parts per million (ppm) and a composition within the ranges specified in the preceding two paragraphs includes the steps of atomising a steel melt of the required chemical composition and annealing the powder produced in an atmosphere comprising hydrogen or dissociated ammonia at a temperature of 700 to 900°C. The annealing atmosphere may be enriched by the addition of carbon monoxide or a hydrocarbon gas such as ethane, methane, butane or propane.

Following annealing, graphite additions may be made to the powder to compensate for carbon losses which may occur during subsequent sintering. The graphite additions are typically from 0.5 to 0.6% by weight. In certain instances, the initial carbon content of the steel may be minimal eg. 0.05% by weight, in which case a graphite addition of approximately 1.3% by weight would be necessary.

The annealed powder, with or without carbon additions, may be compacted to any required shape by isostatic pressing or die compaction.

According to the present invention in another aspect a method of manufacturing heat treated hardened components comprises the steps of atomising an alloy steel melt to produce a powder consisting by weight of up to 1.5% carbon, 1.2 to 2.0%

45

50

55

60

65

70

75

80

85

chromium, less than 0.05% silicon, less than 0.1% manganese and either one or a combination of two or more of the following elements: 0.2 to 1.0% molybdenum, 0.2 to 1.0% nickel, 0 to 0.3% phosphorus, and 0 to 1.0% copper, balance apart from impurities iron, annealing the powder in an atmosphere comprising hydrogen of dissociated ammonia at a temperature of between 700° and 900°C, producing one or more compacts from the annealed powder, sintering the compacts in an atmosphere comprising hydrogen or dissociated ammonia having a dewpoint of less than -10°C at a temperature of between 900 and 1300°C to reduce the oxygen content of the compact to less than 250 parts per million, densifying the sintered compacts to more than 99% of the theoretical density of the material and heat treating the densified components. Graphite additions may be made to the annealed powder prior to sintering to raise its carbon content to a level which, after sintering, will result in a carbon content in the range 0.8 to 1.2% by weight. Densifying of the sintered compacts may be effected by a hot pressing, rolling, forging or extrusion process.

The alloy steel powder may be produced by impinging one or more high velocity water jets onto the surface of a stream of molten steel falling freely under gravity from a vessel. The chemical composition of the powder is generally similar to that required in the final product. Median particle sizes of the as-atomised powder is generally within the range 50 to 100 microns.

As mentioned previously, heat treatable chromium alloy steels conventionally include alloying elements such as silicon and manganese in substantial amounts, i.e. 0.25% and 0.35% by weight respectively. If one produces a powder from such steels, the silicon and manganese alloying elements form oxides during atomisation and the subsequent annealing treatment which are stable and difficult to reduce. As a result, the powder has a high oxide content in the form of oxide inclusions which reduces the ductility, impact strength and fatigue strength of densified compacts produced from the powder. It has been found that oxide inclusions are reduced significantly by reducing the amount of these alloying elements present in the melt; however this is not sufficient in itself as it results in the powder having low hardenability. High hardenability is important if good fatigue and wear resistance properties are to be achieved. Consequently, the silicon and manganese alloying elements are replaced by

appropriate additions of one or a combination of two or more of the elements molybdenum, nickel, phosphorus and copper, all of which have oxidising potentials similar to or less than that of iron and lead to increased hardenability. These additions are in the ranges: molybdenum 0.2 to 1%, nickel 0.2 to 1.0%, phosphorus up to 0.3% and copper up to 1.0%.

The as-atomised powder is annealed in a hydrogen or dissociated ammonia atmosphere at a temperature typically around 800°C to soften the individual particles to improve their compressibility. During annealing, the carbon and oxygen contents of the powder are generally reduced and it is usually necessary, therefore, to add graphite to bring the carbon level up to the required specification of, for example, 0.9 to 1.1% by weight and also to compensate for carbon losses during subsequent sintering. Typically, if the carbon content of the liquid metal before atomisation is approximately 1.0% by weight, up to 0.5% by weight graphite is added.

The annealed powder is formed into compacts related to the required component shape by isostatic pressing or die compaction, which are passed continuously through a furnace on a moving belt and sintered in a hydrogen or dissociated ammonia atmosphere at a temperature typically of 1150°C for approximately  $\frac{1}{2}$  hour. The furnace atmosphere may be enriched by the addition of carbon monoxide or a hydrocarbon gas in order to achieve carbon control during sintering.

Alternatively, the sinter furnace may be a batch furnace or walking beam furnace.

Sintering may also be carried out under subatmospheric pressure conditions at a temperature of approximately 1250°C.

It has been found that in order to reduce the oxide content of the compacts to a minimum, it is necessary to employ furnace atmospheres having dewpoints of less than -10°C preferably less than -20°C. While it would be preferable to operate at the lower dewpoint limit of hydrogen and dissociated ammonia, which as supplied commercially is approximately -70°C, operation of a continuous sinter furnace at dewpoints lower than -40°C is presently not possible and a figure of -20°C is that which can be achieved without resort of the use of expensive sealing mechanisms.

After sintering, the compacts are densified to more than 99% of the theoretical density of the material to form the product components.

After densification, the components may be heat treated by heating to a temperature in the range 800°C to 860°C followed by

70

75

80

85

90

95

100

105

110

115

120

125

130

quenching in oil or water and tempered to give hardness levels in excess of 800 VPM.

Tests carried out on densified articles show that components produced in accordance with the present invention are fully hardened from their centres to their edges at an equivalent bar diameter of 19mm and have hardness levels better than, or at least equivalent to, those possessed by conventional rolled chromium steels.

The invention will now be described with reference to the following two Examples.

#### Example 1

A powder having a median particle size in the range 60 to 80 microns and of nominal composition by weight 1% C, 1.5% Cr, 0.5% Mo, 0.02% Si and 0.05% Mn was produced by water atomisation.

The oxygen content of the as-atomised powder was 5250 ppm which, after annealing in a hydrogen atmosphere at 800°C and slow cooling, reduced to 3100 ppm. The carbon content fell during annealing to 0.75%. The compressibility of the annealed powder was found to be 6.38 gm/cc after compaction at a pressure of 620 MN/m<sup>2</sup>.

Graphite was mixed with the powder to raise the carbon level to approximately 1.3% by weight to compensate for carbon which would be lost during subsequent sintering.

A quantity of the powder was isostatically compacted at a pressure of 210 MN/m<sup>2</sup> to form billets of 75mm diameter which were then sintered for  $\frac{1}{2}$  hr at a temperature of 1150°C in a hydrogen atmosphere of approximately -30°C dewpoint.

After sintering, the billets were hot pressed at a pressure of 1000 MN/m<sup>2</sup> followed by extrusion to 28mm diameter at a pressure of 500 MN/m<sup>2</sup>.

The extruded bars were annealed by heating to 800°C followed by cooling at 10°C per hour down to below 600°C and then air cooled.

The analysis of the extruded bars was found to be by weight 1.07% C, .02% Si, .05% Mn, .008% S, .008% P, .02% Ni, 1.39% Cr and .52% Mo. The oxygen content was 60 ppm which is similar to that normally obtained in wrought low alloy steels.

After heat treatments comprising heating to 840°C followed by oil quenching and tempering at 175°C, hardness levels of 849 VPN and 810 VPN were respectively achieved. Standard wrought carbon-chromium steel samples of the same size subjected to identical heat treatment were found to have hardness levels of 810 VPN and 798 VPN respectively.

#### Example 2

A powder produced by water atomisation

of the same composition as that referred to in Example 1 was annealed and blended with graphite in substantially the same manner as set out in Example 1. A quantity of the annealed powder was isostatically compacted at a pressure of 210 MN/m<sup>2</sup> to form a hollow billet having an external diameter of 75mm and an internal bore of 28mm diameter. The billet was sintered in a hydrogen atmosphere with a dew point of approximately -25°C and subsequently extruded into a length of tube by means of a mandril attached to the extrusion ram, the mandril passing through both the bore of the billet and the extrusion die. The extruded tube had an outer diameter of 31.25mm and the bore an inner diameter of 25mm.

The carbon content of the extruded tube was 1.01% and the oxygen content 150 parts per million.

Samples of the tube were annealed by heating to 800°C followed by cooling at a rate of 10°C per hour to below 600°C and then cooling in air. The annealed hardness of the tube samples was 205 VPN. A number of the annealed samples was hardened by heating to 840°C, quenched in oil and tempered at 175°C. The hardness of the heat treated samples was 870 VPN.

It will be appreciated that components produced from low alloy powders produced in accordance with the method set out above have significantly low oxygen levels, and exhibit good hardness characteristics.

#### WHAT WE CLAIM IS:—

1. A finely divided annealed steel powder consisting by weight of up to 1.5% carbon, 1.0 to 2.0% chromium, less than 0.05% silicon, less than 0.1% manganese and either one or a combination of two or more of the following elements: 0.2 to 1.0% molybdenum, 0.2 to 1.0% nickel, up to 0.3% phosphorus and up to 1.0% copper, the balance, apart from impurities, being iron.

2. A powder as claimed in claim 1 consisting by weight of 0.9 to 1.1% carbon, 1.4 to 1.6% chromium, less than 0.02% silicon, less than 0.05% manganese, and either one or a combination of two or more of the following elements: 0.5 to 0.6% molybdenum, 0.5 to 0.6% nickel, up to 0.2% phosphorus and 0.5 to 0.6% copper, the balance, apart from impurities, being iron.

3. A method of producing a hardenable chromium alloy steel powder having an oxygen content of less than 250 parts per million (ppm) and a composition within the ranges specified in claim 1 or claim 2 including the steps of atomising a steel melt of the required chemical composition and annealing the powder produced in an atmosphere comprising hydrogen or

dissociated ammonia at a temperature of 700 to 900°C.

4. A method as claimed in claim 3 wherein the annealing atmosphere is enriched by the addition of carbon monoxide.

5. A method as claimed in claim 3 wherein the annealing atmosphere is enriched by the addition of a hydrocarbon gas.

6. A method as claimed in claim 5 wherein the hydrocarbon gas comprises ethane, or methane, or butane or propane.

7. A method as claimed in any one of claims 3 to 6 wherein following the annealing step graphite additions are made to the powder to compensate for carbon losses occurring during subsequent sintering.

8. A method as claimed in claim 7 wherein the graphite additions are from 0.5 to 0.6% by weight.

9. A method of manufacturing heat treated hardened components comprising the steps of atomising an alloy steel melt to produce a powder consisting by weight of up to 1.5% carbon, 1.2 to 2.0% chromium, less than 0.05% silicon, less than 0.1% manganese and either one or a combination of two or more of the following elements: 0.2 to 1.0% molybdenum, 0.2 to 1.0% nickel, 0 to 0.3% phosphorus, and 0 to 1.0% copper, balance apart from impurities iron, annealing the powder in an atmosphere comprising hydrogen or dissociated ammonia at a temperature of between 700 and 900°C, producing one or more compacts from the annealed powder, sintering the compacts in an atmosphere comprising hydrogen or dissociated

ammonia having a dewpoint of less than -10°C at a temperature of between 900 and 1300°C to reduce the oxygen content of the compact to less than 250 parts per million, densifying the sintered compacts to more than 99% of the theoretical density of the material and heat treating the densified components.

10. A method as claimed in claim 9 wherein graphite additions are made to the annealed powder prior to sintering to raise its carbon content to a level which, after sintering, will result in a carbon content in the range 0.8 to 1.2% by weight.

11. A method as claimed in claim 9 or claim 10 wherein the sintered compacts are densified by either a hot pressing, rolling, forging or extrusion process.

12. A method as claimed in any one of claims 9 to 11 wherein the alloy steel melt is atomised by impinging one or more high velocity water jets on to the surface of a stream of the melt falling freely under gravity from a vessel.

13. Compacts manufactured from an annealed powder as claimed in claim 1 or claim 2.

14. A method of producing chromium alloy steel powders substantially as herein described with reference to either one of the Examples set out in the complete specification.

15. A chromium alloy steel powder produced by a method described in either one of the examples set out in the complete specification.

M. J. HOOLAHAN,  
Agent for the Applicants.